



INTERNATIONAL  
GEMOLOGICAL  
INSTITUTE

**ELECTRONIC COPY**

**LABORATORY GROWN DIAMOND REPORT**

September 16, 2025

IGI Report Number **LG734543030**

Description **LABORATORY GROWN DIAMOND**

Shape and Cutting Style **PRINCESS CUT**

Measurements **6.61 X 6.59 X 4.66 MM**

**GRADING RESULTS**

Carat Weight **1.79 CARAT**

Color Grade **D**

Clarity Grade **VVS 1**

**ADDITIONAL GRADING INFORMATION**

Polish **EXCELLENT**

Symmetry **EXCELLENT**

Fluorescence **NONE**

Inscription(s) **IGI LG734543030**


Comments: As Grown - No indication of post-growth treatment.

This Laboratory Grown Diamond was created by High Pressure High Temperature (HPHT) growth process.


Type II

LG734543030  
Report verification at [igi.org](http://igi.org)

**PROPORTIONS**



**CLARITY CHARACTERISTICS**



**KEY TO SYMBOLS**

Red symbols indicate internal characteristics.

Green symbols indicate external characteristics.

LABORATORY GROWN DIAMOND REPORT



September 16, 2025

IGI Report Number **LG734543030**

Description **LABORATORY GROWN DIAMOND**

Shape and Cutting Style **PRINCESS CUT**


Measurements **6.61 X 6.59 X 4.66 MM**

**GRADING RESULTS**


Carat Weight **1.79 CARAT**

Color Grade **D**

Clarity Grade **VVS 1**



Sample Image Used



**ADDITIONAL GRADING INFORMATION**

Polish **EXCELLENT**

Symmetry **EXCELLENT**

Fluorescence **NONE**

Inscription(s) **IGI LG734543030**

Comments: As Grown - No indication of post-growth treatment.

This Laboratory Grown Diamond was created by High Pressure High Temperature (HPHT) growth process.

Type II

[www.igi.org](http://www.igi.org)

© IGI 2020, International Gemological Institute



September 16, 2025

IGI Report No. LG734543030

PRINCESS CUT

6.61 X 6.59 X 4.66 MM

1.79 CARAT

D

VVS 1

70.7%

68%

Medium

Pointed

EXCELLENT

EXCELLENT

NONE

IGI LG734543030

Comments: As Grown - No indication of post-growth treatment.

This Laboratory Grown Diamond was created by High Pressure High Temperature (HPHT) growth process.

Type II



FD - 10 20