



INTERNATIONAL
GEMOLOGICAL
INSTITUTE

ELECTRONIC COPY

LABORATORY GROWN DIAMOND REPORT

September 4, 2026

IGI Report Number

LG835670873

Description

LABORATORY GROWN DIAMOND

Shape and Cutting Style

ROUND BRILLIANT

Measurements

7.51 - 7.57 X 4.58 MM

GRADING RESULTS

Carat Weight

1.59 CARAT

Color Grade

D

Clarity Grade

VS 1

Cut Grade

IDEAL

ADDITIONAL GRADING INFORMATION

Polish

EXCELLENT

Symmetry

EXCELLENT

Fluorescence


NONE

Inscription(s)

 LG835670873

Comments: As Grown - No indication of post-growth treatment.
This Laboratory Grown Diamond was created by High Pressure High Temperature (HPHT) growth process.
Type II

PROPORTIONS



Medium (Faceted)


59%

34.7°

40.8°

60.8%

Pointed



Sample Image Used

COLOR

D E F G H I J Faint Very Light Light

CLARITY

FL IF VVS¹⁻² VS¹⁻² SI¹⁻² I¹⁻³

Flawless Internally Flawless Very Very Slightly Included Very Slightly Included Slightly Included Included



© IGI 2020, International Gemological Institute

FD - 10 20

LABORATORY GROWN DIAMOND REPORT



September 4, 2026

IGI Report Number

LG835670873

Description

LABORATORY GROWN DIAMOND

Shape and Cutting Style

ROUND BRILLIANT

Measurements

7.51 - 7.57 X 4.58 MM

GRADING RESULTS

Carat Weight

1.59 CARAT

Color Grade

D

Clarity Grade

VS 1

Cut Grade

IDEAL

ADDITIONAL GRADING INFORMATION

Polish

EXCELLENT

Symmetry

EXCELLENT


Fluorescence

NONE

Inscription(s)

 LG835670873

Comments: As Grown - No indication of post-growth treatment.
This Laboratory Grown Diamond was created by High Pressure High Temperature (HPHT) growth process.
Type II



Medium (Faceted)

59%

34.7°

40.8°

60.8%

Pointed



IGI

September 4, 2026

IGI Report No LG835670873

ROUND BRILLIANT

7.51 - 7.57 X 4.58 MM

1.59 CARAT

D

VS 1

IDEAL

60.8%

59%

Medium (Faceted)

Pointed

EXCELLENT

EXCELLENT

NONE

 LG835670873

Cutler

Polish

Symmetry

Fluorescence

Inscriptions(s)

Comments: As Grown - No indication of post-growth treatment.
This Laboratory Grown Diamond was created by High Pressure High Temperature (HPHT) growth process.
Type II

www.igi.org